

Rubber Process and Extender Oil

Descriptions

- *PTT Rubflex 105, 111, 130*: are used as raw materials for particular products, produced from high quality paraffinic base oils.

Special Properties

- Good thermal and oxidation stability.
- High viscosity index
- High flash point and low volatility.
- Exhibit good color stability.

Applications

- Suitable for use in production processes which have mineral oils as component of the products.
- Can be used as economical once through lubricating oils for light duty applications.

Reference Standards

Typical Properties

	105	111	130
- Density @ 15 °C, g/cm ³	0.8685	0.8873	0.9011
- Viscosity @ 40 °C, cSt	29.38	98.88	471.1
- Viscosity @ 100 °C, cSt	5.161	11.00	31.03
- Viscosity Index	104	95	95
- Flash Point, °C	221	265	303
- Pour Point, °C	-9	-9	-9
- Aniline Point, °C	102	107	121
- Color, ASTM	L0.5	L1.0	L1.5
- Carbon Type Analysis, %			
C _A	6.6	8.0	8.5
C _N	29.1	26.8	25.7
C _P	64.3	65.2	65.8

For more information, contact Fuels & Lubricants Research department, PTT Research and Technology Institute PTT Public Company Limited. Tel: 0-2537-3000 Ext. 8408 Fax : 0-2537-3000 Ext. 8286 Technical Service Division Tel : 0-2239-7908, 0-2239-7986, 0-2239-7987