



PTT Hikut semi W 30

Semi-synthetic cutting fluid

Descriptions

- *PTT Hikut semi W 30* : The product is formulated from medium lubricity and biostable additives. It is suitable for machining mild steel and other general metals. The concentrate color is brown when dilute with water the color is white translucent.

Special Properties

- Good lubricity properties.
- Good cooling or remove heat during machining.
- Good rust and corrosion prevention.
- Resistance to foaming.
- Resistance to bacterial and fungal growth.
- No toxic substance such as Chlorine and Nitrate / Nitrite

Application

- Recommended concentration (%). (Dilution with water)

Metal / Process	Drilling	Milling	Tapping	Reaming
Cast Iron	4-6%	4-6%	6-8%	8-10%
Mild Steel	4-6%	4-6%	6-8%	8-10%
Alloy Steel	6-8%	6-8%	8-10%	10-12%

Typical Value

- | | |
|------------------------------|------------------|
| - Appearance | Brown |
| - Viscosity @ 40 °C, cSt | 65.30 |
| - pH (Dilution 1 : 20) | 9.00 |
| - Rust test / IP287 | 3.0% break point |
| - Emulsion stability / IP263 | Pass |
| - Thermal stability / IP311 | Good homogeneous |
| - Nitrate / Nitrite | none |
| - Chlorine | none |

For more information, contact Fuel and Lubricant Department , PTT Research and Technology Institute, PTT Public Company Limited Tel 0-2537-3000 Ext 8182 and 8270 Fax 0-2537-3000 Ext 8146 โทร 8199